

COMBUSTION MODIFIED STANDARD POLYURETHANE FOAM (CME)

Foam properties	CV 2130	CV 2533	CV 3025	CV 3037	CV 3223	CV 3538	Test method
Rel. density (net), kg/m ³	19 - 22	23 – 26	28 - 31	28 - 31	30 - 33	33 - 36	ISO 845
Hardness, (ILD 40 %), N	105 - 140	115 - 160	96 - 144	135 - 180	80 - 125	150 - 195	ISO 2439
Compression set, (50%, 22 h, 70 °C) %, max	20	10	12	6	6	9	ISO 1856
Colour	white	white	white	white	yellow	white	
Meets to the requirements of the standard	BS 5852 : Part 2: 1982 (Crib5) (Schedule 1: Part 1)						

International marking Vita Baltic marking
CME = CV